



ISO-9001 Registered Quality System.
ISO-21469 Compliant.

Sales, Service & Distribution Center

Newark, NJ 07105
Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605
Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

PRODUCT DATA

LUBRIPLATE SYNXTREME HD SERIES

"These products are certified OU Kosher Pareve – Synxtreme HD-2 & Synxtreme HD-1"

DESCRIPTION

LUBRIPLATE SYNXTREME HD greases are 100% synthetic, calcium sulfonate complex based. This advanced technology delivers outstanding shear stability, reduced wear and excellent resistance to water and other corrosive substances. The synthetic fluid used in these greases delivers increased oxidation stability and enables them to be effective at application temperatures up to 400°F with frequent re-lubrication intervals.

APPLICATIONS

LUBRIPLATE SYNXTREME HD greases are outstanding lubricants for all types of anti-friction bearings, which are subjected to wide operating temperature ranges.

ADVANTAGES

- ⇒ Mechanical stability – the greases do not thin out
- ⇒ Deliver excellent anti-wear (AW) and extreme pressure (EP) protection
- ⇒ Calcium sulfonate thickener delivers unsurpassed rust and corrosion prevention
- ⇒ Excellent resistance to chemically treated water wash down procedures at high temperatures
- ⇒ Delivers lubricant consolidation because of their multi-use capability

Typical Test Data

PROPERTY	TEST METHOD	TYPICAL RESULTS		
		HD-2	HD-1	HD-0
Thickener		Calcium Sulfonate Complex	Calcium Sulfonate Complex	Calcium Sulfonate Complex
NLGI Grade	D-217	2	1	0
Color	Visual	Tan	Tan	Tan
Texture	Visual	Smooth	Smooth	Smooth
Dropping Point	D-2265	>600°F	>600°F	>600°F
Unworked Penetration	D-217	277	314	349
Worked Penetration 60X	D-217	280	318	361
Oil Separation - % Loss	D-1742	0.0	0.0	N/A
Water Washout @ 175°F	D-1264	<0.5	<0.5	<0.5
Rust Prevention Properties	D-1743	Pass	Pass	Pass
Four Ball Wear	D-2266	0.45mm	0.50mm	0.58mm
Evaporation Loss	D-972	0.11	0.11	0.18
4-Ball EP - Weld Load	D-2596	420 kg	400 kg	315 kg
Oxidation Stability	D-942	-1 psi	-1 psi	0 psi
Base Fluid Type		PAO	PAO	PAO
ISO VG		100	100	100
Viscosity @ 40°C - cSt	D-445	90 - 110	90 - 110	90 - 110
Cold Test		-40°F	-40°F	-40°F

PACKAGING AVAILABLE

	HD-2	HD-1	HD-0
35 lb. Pail	L0401-035	L0402-035	L0403-035
120 lb. Quarter Size Drum	L0401-039	L0402-039	L0403-039
415 lb. Full Size Drum	L0401-040	L0402-040	L0403-040
Carton, 40/16 oz. Cartridges	L0401-098	***	***
Carton, 40/15.5 oz. Cartridges	***	L0402-098	***

