

ISO-9001 Registered Quality System. ISO-21469 Compliant. Sales, Service & Distribution Center Newark, NJ 07105 Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center Toledo, OH 43605 Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support Phone: 1-800-733-4755

LUBRIPLATE Neptune Launching Base Coat

LUBRIPLATE Neptune Launching Base Coat has been used for many decades to launch virtually every type of ship from aircraft carriers to barges. LUBRIPLATE Neptune Launching Base Coat will sustain loads of more than ten tons per square foot at 70°F and can be used in combination with LUBRIPLATE Neptune Launching Slip Coat.

Typical Properties

Melting Point	150°F
Flash Point	430°F
Specific Gravity	0.91
Color	Light Blue
Appearance at 70°F	Hard Wax

Prior to the application of Base Coat, the ways should be thoroughly dried. Base Coat will not properly adhere to wet or damp ways. Base Coat must be poured while hot. It should be heated to a temperature sufficiently high so that it is still in a liquid state at the point of application. Lamination can be avoided by pouring small areas at a time. The desired thickness should be achieved while the Base Coat is still hot. Base Coat is typically applied ¹/₄" to ¹/₂" thick, but never less than ¹/₈". Upon completion of applying the Base Coat, LUBRIPLATE Neptune Launching Slip Coat may then be applied.

<u>Coverage</u>			
Thickness <u>In Inches</u>	Pounds Required to Cover 1 Square Foot <u>(Approx.)</u>	Drum (About 325 lbs.) Will Cover Square Feet <u>(Approx.)</u>	
1/8	.65	500	
1/4	1.35	241	
1/2	2.66	122	

Packaging Available	<u>Part No.</u>
45 lb. Box	L0214-035
325 lb. Fiber Drums	L0214-040

Printed in USA Revised 11/21/2014